


Satish Enterprise Pvt. Ltd.



**AUTHORISED
DEALERS:**



Raychem  **RPG**
Heat Shrinkable Jointing Kits

301, Elphinstone House, 17, Murzban Road, Opp. Sterling Cinema, Fort, Mumbai - 400 001.
Tel. : 6120 9191 • 2207 6434/35 • E-mail : office@satishent.com • satishent@mtnl.net.in
Website : www.satishent.com • CIN : U74900MH2012PTC226919

Aluminium Rods Specification

Particulars	EC 1350 (H12)
Specified Diameter	9.52mm
Tensile & Elongation	8.5 ~ 11.9 kgf/mm ³
Conductivity & Resistivity	61.5% IACS

Element	Composition (%)
Silicon	Max: 0.10
Iron	Max: 0.40
Copper	Max: 0.05
Manganese	Max: 0.01
Chromium	Max: 0.01
Zinc	Max: 0.05
Boron	Max: 0.05
Gallium	Max: 0.03
Vanadium & Titanium	Max: 0.02
Other elements, each	Max: 0.03
Other elements, total	Max: 0.10
Aluminium	Min: 99.5