

Satish Enterprise Pvt. Ltd.

AUTHORISED
DEALERS:



Raychem **RPG**
Heat Shrinkable Jointing Kits

301, Elphinstone House, 17, Murzban Road, Opp. Sterling Cinema, Fort, Mumbai - 400 001.
Tel. : 6120 9191 • 2207 6434/35 • E-mail : office@satishent.com • satishent@mtnl.net.in
Website : www.satishent.com • CIN : U74900MH2012PTC226919

Aluminium Ingots Specification												
Grade		% Al	% Fe	% Si	Constituents							
					Li %	Ni %	Cr %	Ti %	Zn %	Mg %	Mn %	Cu %
P0610	Min	99.84	0.09	0.04	Trace	Trace	Trace	Trace	Trace	Trace	Trace	Trace
	Max	99.84	0.1	0.06	0.0005	0.002	0.0015	0.004	0.004	0.003	0.0003	0.0003
	Avg	99.84	0.095	0.05	0.0004	0.0017	0.001	0.004	0.003	0.002	0.0002	0.0002
P1015	Min	99.75	0.1	0.04	Trace	Trace	Trace	Trace	Trace	Trace	Trace	Trace
	Max	99.84	0.15	0.1	0.0008	0.0045	0.001	0.007	0.006	0.005	0.001	0.0006
	Avg	99.78	0.13	0.06	0.0005	0.0025	0.001	0.005	0.003	0.002	0.0006	0.0004
P1020	Min	99.7	0.14	0.04	Trace	Trace	Trace	Trace	Trace	Trace	Trace	Trace
	Max	99.77	0.2	0.1	0.002	0.005	0.004	0.007	0.006	0.005	0.0015	0.0015
	Avg	99.72	0.17	0.07	0.0005	0.003	0.001	0.005	0.003	0.001	0.0008	0.0005